QF Floor Sweep

TECHNICAL DATA

Ø mm	Collar Rolled Edge (nom. mm.)	X mm	Length mm	Y mm	Weight kg	Galvanised Steel
80	6	305	408	155	0,6	0,7
100	6				1,0	
125	6				2,0	
140	6				2,9	
150	6				3,4	
160	6				3,8	
180	8				4,9	
200	8				5,9	
224	8				6,9	
250	8				8,3	
300	10				10,7	

Temperature Rating of Product Components						
° C	Floor Sweep	Sealants				
200°						
121° -20°	Galvanised Steel	Joka Seal Metal Sealant 2315				

At temperatures ranging between 200° C and 250° C, the zinc-
iron alloy layers in galvanised steel will continue to provide a
high level of protection from corrosion. However, there may be

iron alloy layers high level of pro some peeling, changes in mechanical properties, and reduction in the corrosion protection. Recommended max. service temperature is 200° C.

Additional Notes

Compliance / Rating of Product Components					
Product	Material	Compliance / Rating			
Floor Sweep	Galvanised	DX51D with Z275 Coating			
Joka Seal Metal Sealant 2315	Acetone blend	AAMA Specification 801.1			

Construction

Body: lapped, spot welded and caulked. Collars: have a laser welded longitudinal seam. Collars are

attached to the body using a raised hemmed, spot welded seamed construction and are caulked.

Standard QF end can be changed to Raw ID (I/D), Raw OD (O/D), Hose Adapter (FX), Flat Bar Flange (FL), or 6mm turned out edge







